



TEXPRINT DISCHARGE BASE

Code: AM100609

Water based product for textile discharge printing, suitable for cotton dyed with dischargeable pigments.

GENERAL CHARACTERISTICS

- It contains fillers on the formulation that permits to obtain discharge effect even on fabric partially dischargeable.
- Wet on wet printing

PREPARATION

Prepare only the quantity needed for daily use:

- Texprint discharge base grms. 1.000
- Colorante (pigment) grms. 0.050
- Texprint discharge corrodente grms. 0.050

The mixed paste has a stability of 12 hours. CORRODENTE has to be added always at the last. The percentage of CORRODENTE can be increased up to max 10%.

PRINTING

To obtain best results use screens 43 threads/cm both for manual printing and automatic.

POLIMERIZATION

To obtain a perfect corrosion put garments still wet in the oven immediately after printing.

To obtain high washing resistance put in the oven at 150-160°C for 2/3 minutes.

The polymerization develops phormaldeyde, for this reason we suggest to wash the garment before wearing or give this information to final customer.

ADDITIVES

TEXPRINT ADDENSANTE W

Thickening agent (add 0,5-3%)

TEXPRINT RITARDANTE GEL to slow drying on the screen (add 5%)

TEXPRINT ADDITIVO S to slow drying on the screen without reducing the viscosity (add 5%)

TEXPRINT NO TACK

To obtain a more opaque and softer touch (add 15-20%).

CLEANING

Wash tools with water.

PACKING

60 KG.

NOTE

Before to use the ink in production, we suggest to make some test in order to evaluate if the product satisfies the requirement.

Amex srl gives the a/m suggestions as guidelines for the customer and assumes no liability direct or indirect for any improper use. It is the user's responsibility to determine the suitability of the product to the intended use according to his working conditions.

MANUFACTURER- **A.MANOUKIAN.EXP.SRL** , Appiano Gentile (CO) ITALY

DISTURBUTER- **KOTONLAYN TEKS.KONF SN TC LTD ŞTI. BURSA-TURKEY**
TEL-0-224-2113331 FAX 0-224-2113332