



## SCREEN CHEMICALS

**TRANSPARENT CERAMIC LACQUER** (cod.162320)

**THINNER FOR CERAMIC LACQUER** (cod. 152512)

Technical data sheet N° 14/CER

1<sup>st</sup> July 2005

CERAMIC

Hydrohardening mono-component polyurethanic lacquer, devised to protect ceramic screens.  
The qualities of VERNICE TRASPARENTE PER CERAMICA are the following:

- Chemical and physical resistance as well as good elasticity
- Mono-component: no catalyzing process required
- Hydrohardening

**PREPARATION** : **Dilute the lacquer with the special thinner DILUENTE PER VERNICE CERAMICA in 30% volume ratio.**

**APPLICATION** : *Screen protection* :  
apply the lacquer on both sides of the screen.  
Treat the screen with a sucking machine only on its printing side, to eliminate the lacquer that covers the engraved design.

*Screen improvement* :  
apply the lacquer only on the squeegee side.  
Treat the screen with a sucking machine only on its printing side, to eliminate the lacquer that covers the engraved design and let the screen dry completely .

Apply the lacquer only on the printing side with a brush so as to get the required thickness. In other words, treat the screen with a sucking machine only on its squeegee side to eliminate the lacquer that covers the engraved design.

**HARDENING** : Hardening occurs after about 3 hours. Room humidity: 70%  
Chemical and physical resistance will be reached after about 24 hours.

**CLEANING** : Use SOLVENTE 505 - 151505, or SOLVENTE LAVAGGIO 460 - 151460.  
Do never let the product dry on tools, otherwise it may not be removable, once hardened.

Information contained in this Technical Data Sheet constitute the result of tests carefully carried out and express our best as well as most up-dated know-how. Nevertheless these news are published only as information and can't neither engage the responsibility of our company nor provide a whatsoever pretext for disputes of any kind, which could any how be connected to the usage of above described products. In consideration of the above the usage conditions are not under our control.

**KIIAN S.R.L. – Via A. De Gasperi, 1 – 22070 LUISAGO (CO)**  
**Tel: + 39 031 9090111 – Fax: +39 031 920505 e-mail: info@kiian.it**



## SCREEN CHEMICALS

### **WARNING :**

With the lacquer VERNICE TRASPARENTE PER CERAMICA, it is important to keep in mind the following standards:

- Moisture sensitive
- Open with care: there could be some overpressure inside
- Keep the packages perfectly closed, far from flames, sparkles or heat sources
- Follow the specific indications for isocyanate products

**PACKAGING :**

- TRANSPARENT VARNISH FOR CERAMIC cod. 162320 in 5 kg packaging.
- THINNER FOR VARNISH CERAMIC cod. 152512 in 5 liter packaging

MIX WELL BEFORE USE  
AFTER USE, CLOSE IT CAREFULLY IN ITS CONTAINER

Ask for the safety data sheet for instructions.

Information contained in this Technical Data Sheet constitute the result of tests carefully carried out and express our best as well as most up-dated know-how. Nevertheless these news are published only as information and can't neither engage the responsibility of our company nor provide a whatsoever pretext for disputes of any kind, which could any how be connected to the usage of above described products. In consideration of the above the usage conditions are not under our control.

**KIIAN S.R.L. – Via A. De Gasperi, 1 – 22070 LUISAGO (CO)**  
**Tel: + 39 031 9090111 – Fax: +39 031 920505 e-mail: [info@kiian.it](mailto:info@kiian.it)**